

PROPERTY	TEST METHOD	FREQUENCY ⁽¹⁾	UNIT Metric	Solmax 430G-9000	Solmax 440G-9000	Solmax 460G-9000	Solmax 480G-9000	Solmax 500G-9000
SPECIFICATIONS								
Thickness (min. avg.)	ASTM D-5199	Every roll	mm	0.75	1.00	1.50	2.00	2.50
Thickness (min.)	ASTM D-5199	Every roll	mm	0.68	0.90	1.35	1.80	2.25
Sheet Density (8)	ASTM D-792	Every 10 rolls	g/cc	≥ 0.940	≥ 0.940	≥ 0.940	≥ 0.940	≥ 0.940
Carbon Black Content (9)	ASTM D-4218	Every 2 rolls	%	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0
Carbon Black Dispersion	ASTM D-5596	Every 10 rolls	Category	Cat. 1 & Cat. 2	Cat. 1 / Cat. 2	Cat. 1 / Cat. 2	Cat. 1 / Cat. 2	Cat. 1 / Cat. 2
OIT - standard (avg.)	ASTM D-3895	1/Batch	min	100	100	100	100	100
Tensile Properties (min. avg) (2)	ASTM D-6693	Every 2 rolls						
Strength at Yield			kN/m	11.5	15	22	31	37
Elongation at Yield			%	13	13	13	13	12
Strength at Break			kN/m	21	28	42	57	67
Elongation at Break			%	700	700	700	700	700
Tear Resistance (min. avg.)	ASTM D-1004	Every 5 rolls	N	93	125	187	250	311
Puncture Resistance (min. avg.)	ASTM D-4833	Every 5 rolls	N	265	355	540	695	800
Dimensional Stability	ASTM D-1204	Per formulation	%	± 2	± 2	± 2	± 2	± 2
Stress Crack Resistance (SP-NCTL)	ASTM D-5397	1/Batch	hr	400	400	400	400	400
Oven Aging - % retained after 90 days	ASTM D-5721	Per formulation (5						
HP OIT (min. avg.)	ASTM D-5885		%	80	80	80	80	80
UV Resistance - % retained after 1600 hr	GRI-GM-11	Per formulation (5						
HP-OIT (min. avg.)	ASTM D-5885		%	50	50	50	50	50
SUPPLY SPECIFICATIONS (Roll dimensions may vary ±1%)								
Roll Dimension - Width	-		m	7.50	7.50	7.50	7.50	7.50
Roll Dimension - Length	-		m	280.0	210.0	140	105.0	85.0
Area (Surface/Roll)	-		m ²	2100	1575	1050	787.5	637.5
Color (one side) (4)	-	-		Green	Green	Green	Green	Green

NOTES

1. Testing frequency based on standard roll dimensions and one batch is approximately 180,000 lbs (or one railcar).
2. Machine Direction (MD) and Cross Machine Direction (XMD or TD) average values should be on the basis of 5 specimens each direction.
4. No smooth edge. The green layer may cause the carbon black content results to be 3% higher than specified on the data sheet.
5. Certified by black formulation on geomembrane roll or molded plaque
8. Correlation table is available for ASTM D792 vs ASTM D1505. Both methods give the same results.
9. Correlation table is available for ASTM D1603 vs ASTM D4218. Both methods give the same results.

* All values are nominal test results, except when specified as minimum or maximum.

* The information contained herein is provided for reference purposes only and is not intended as a warranty of guarantee. Final determination of suitability for use contemplated is the sole responsibility of the user. SOLMAX assumes no liability in connection with the use of this information.

PROPERTY	TEST METHOD	FREQUENCY ⁽¹⁾	UNIT Metric	Solmax 430GST-9000	Solmax 440GST-9000	Solmax 460GST-9000	Solmax 480GST-9000	Solmax 500GST-9000
SPECIFICATIONS								
Thickness (min. avg.)	ASTM D-5994	Every roll	mm	0.75	1.00	1.50	2.00	2.50
Lowest individual for 10 out of 10 values			mm	0.68	0.90	1.35	1.80	2.25
Asperity Height (min. avg.) (3)	ASTM D-7466	Every roll	mm	0.40	0.45	0.45	0.45	0.45
Sheet Density (8)	ASTM D-792	Every 10 rolls	g/cc	> 0.94	≥ 0.940	≥ 0.940	≥ 0.940	≥ 0.940
Carbon Black Content (9)	ASTM D-4218	Every 2 rolls	%	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0
Carbon Black Dispersion	ASTM D-5596	Every 10 rolls	Category	Cat. 1 / Cat. 2	Cat. 1 / Cat. 2	Cat. 1 / Cat. 2	Cat. 1 / Cat. 2	Cat. 1 & Cat. 2
OIT - standard (avg.)	ASTM D-3895	1/Batch	min	100	100	100	100	100
Tensile Properties (min. avg) (2)	ASTM D-6693	Every 2 rolls						
Strength at Yield			kN/m	11	15.3	23	30	37
Elongation at Yield			%	12	13	13	13	12
Strength at Break			kN/m	8	15.3	23	30	26
Elongation at Break			%	200	200	200	200	200
Tear Resistance (min. avg.)	ASTM D-1004	Every 5 rolls	N	93	130	200	267	311
Puncture Resistance (min. avg.)	ASTM D-4833	Every 5 rolls	N	200	400	530	667	667
Dimensional Stability	ASTM D-1204	Per formulation	%	± 2	± 2	± 2	± 2	± 2
Stress Crack Resistance (SP-NCTL)	ASTM D-5397	1/Batch	hr	400	400	400	400	400
Oven Aging - % retained after 90 days	ASTM D-5721	Per formulation (5						
HP OIT (min. avg.)	ASTM D-5885		%	80	80	80	80	80
UV Resistance - % retained after 1600 hr	GRI-GM-11	Per formulation (5						
HP-OIT (min. avg.)	ASTM D-5885		%	50	50	50	50	50
SUPPLY SPECIFICATIONS (Roll dimensions may vary ±1%)								
Roll Dimension - Width	-		m	7.50	7.50	7.50	7.50	7.50
Roll Dimension - Length	-		m	250.0	200.0	135.0	105.0	85.0
Area (Surface/Roll)	-		m ²	1875	1500	1012.5	787.5	637.5
Color (one side) (4)	-	-		Green	Green	Green	Green	Green

NOTES

1. Testing frequency based on standard roll dimensions and one batch is approximately 180,000 lbs (or one railcar).
2. Machine Direction (MD) and Cross Machine Direction (XMD or TD) average values should be on the basis of 5 specimens each direction.
3. Of 10 readings; 8 out of 10 must be >7 mils (0.18 mm), and lowest individual reading must be >5 mils (0.13 mm). ASTM D7466 is identical to GRI-GM12.
4. Black or grey spots may be visible on the textured surface. No smooth edge. The green layer may cause the carbon black content results to be 3% higher than specified on the data sheet.
5. Certified by black formulation on geomembrane roll or molded plaque
8. Correlation table is available for ASTM D792 vs ASTM D1505. Both methods give the same results.
9. Correlation table is available for ASTM D1603 vs ASTM D4218. Both methods give the same results.

* All values are nominal test results, except when specified as minimum or maximum.

* The information contained herein is provided for reference purposes only and is not intended as a warranty of guarantee. Final determination of suitability for use contemplated is the sole responsibility of the user. SOLMAX assumes no liability in connection with the use of this information.

Solmax International Inc., 2801 Boul. Marie-Victorin, Varennes, Qc, Canada, J3X 1P7
 Tel.: (450) 929-1234 Fax: (450) 929-2550 www.solmax.com

PROPERTY	TEST METHOD	FREQUENCY ⁽¹⁾	UNIT Metric	Solmax 430GT-9000	Solmax 440GT-9000	Solmax 460GT-9000	Solmax 480GT-9000	Solmax 500GT-9000
SPECIFICATIONS								
Thickness (min. avg.)	ASTM D-5994	Every roll	mm	0.75	1.00	1.50	2.00	2.50
Lowest individual for 10 out of 10 values			mm	0.68	0.90	1.35	1.80	2.25
Asperity Height (min. avg.) (3)	ASTM D-7466	Every roll	mm	0.40	0.45	0.45	0.45	0.45
Sheet Density (8)	ASTM D-792	Every 10 rolls	g/cc	> 0.94	≥ 0.940	≥ 0.940	≥ 0.940	≥ 0.940
Carbon Black Content (9)	ASTM D-4218	Every 2 rolls	%	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0
Carbon Black Dispersion	ASTM D-5596	Every 10 rolls	Category	Cat. 1 / Cat. 2	Cat. 1 / Cat. 2	Cat. 1 / Cat. 2	Cat. 1 / Cat. 2	Cat. 1 & Cat. 2
OIT - standard (avg.)	ASTM D-3895	1/Batch	min	100	100	100	100	100
Tensile Properties (min. avg) (2)	ASTM D-6693	Every 2 rolls						
Strength at Yield			kN/m	11.5	15.3	23	30	37
Elongation at Yield			%	13	13	13	13	12
Strength at Break			kN/m	11.5	15.3	23	30	26
Elongation at Break			%	200	200	200	200	200
Tear Resistance (min. avg.)	ASTM D-1004	Every 5 rolls	N	102	130	200	267	311
Puncture Resistance (min. avg.)	ASTM D-4833	Every 5 rolls	N	265	400	530	667	667
Dimensional Stability	ASTM D-1204	Per formulation	%	± 2	± 2	± 2	± 2	± 2
Stress Crack Resistance (SP-NCTL)	ASTM D-5397	1/Batch	hr	400	400	400	400	400
Oven Aging - % retained after 90 days	ASTM D-5721	Per formulation (5						
HP OIT (min. avg.)	ASTM D-5885		%	80	80	80	80	80
UV Resistance - % retained after 1600 hr	GRI-GM-11	Per formulation (5						
HP-OIT (min. avg.)	ASTM D-5885		%	50	50	50	50	50
SUPPLY SPECIFICATIONS (Roll dimensions may vary ±1%)								
Roll Dimension - Width	-		m	7.50	7.50	7.50	7.50	7.50
Roll Dimension - Length	-		m	250.0	190.0	135.0	105.0	85.0
Area (Surface/Roll)	-		m ²	1875	1425	1012.5	787.5	637.5
Color (one side) (4)	-	-		Green	Green	Green	Green	Green

NOTES

1. Testing frequency based on standard roll dimensions and one batch is approximately 180,000 lbs (or one railcar).
2. Machine Direction (MD) and Cross Machine Direction (XMD or TD) average values should be on the basis of 5 specimens each direction.
3. Of 10 readings; 8 out of 10 must be >7 mils (0.18 mm), and lowest individual reading must be >5 mils (0.13 mm). ASTM D7466 is identical to GRI-GM12.
4. Black or grey spots may be visible on the textured surface. No smooth edge. The green layer may cause the carbon black content results to be 3% higher than specified on the data sheet.
5. Certified by black formulation on geomembrane roll or molded plaque
8. Correlation table is available for ASTM D792 vs ASTM D1505. Both methods give the same results.
9. Correlation table is available for ASTM D1603 vs ASTM D4218. Both methods give the same results.

* All values are nominal test results, except when specified as minimum or maximum.

* The information contained herein is provided for reference purposes only and is not intended as a warranty of guarantee. Final determination of suitability for use contemplated is the sole responsibility of the user. SOLMAX assumes no liability in connection with the use of this information.