



PYRAMAT[®] high performance turf reinforcement mat (HPTRM) is a three-dimensional, lofty, woven polypropylene geotextile that is available in green or tan which is specially designed for erosion control applications on steep slopes and vegetated waterways. The matrix is composed of polypropylene monofilament yarns **featuring X3[®] technology** woven into a uniform configuration of resilient pyramid-like projections. The material exhibits very high interlock and reinforcement capacity with both soil and root systems, demonstrates superior UV resistance, and enhances seedling emergence.

PYRAMAT conforms to the property values listed below¹ and is manufactured at a Propex facility having achieved ISO 9001:2000 certification. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). This product is NTPEP approved for AASHTO standards.

MARV ²			
PROPERTY	TEST METHOD	ENGLISH	METRIC
ORIGIN OF MATERIALS			
% U.S. Manufactured Inputs		100%	100%
% U.S. Manufactured		100%	100%
PHYSICAL			
Mass/Unit Area	ASTM D-6566	13.5 oz/yd ²	457.7g/m ²
Thickness	ASTM D-6525	0.4 in	10.2 mm
Light Penetration (% Passing)	ASTM D-6567	15% (Max)	15% (Max)
Color	Visual	Green or Tan	
MECHANICAL			
Tensile Strength (Grab)	ASTM D-6818	4000 x 3000 lb/ft	58.4 x 43.8 kN/m
Elongation	ASTM D-6818	40 x 35%	40 x 35%
Resiliency	ASTM D-6524	80%	80%
Flexibility	ASTM D-6575	0.534 in-lb (avg)	615,000 mg-cm (avg)
ENDURANCE			
UV Resistance % Retained 6000 hrs	ASTM D-4355	90%	90%
UV Resistance % Retained 10000 hrs	ASTM D-4355	85%	85%
PERFORMANCE			
Velocity ³ (Fully Vegetated)	Large Scale	25 ft/sec	7.6 m/sec
Shear Stress ³ (Fully Vegetated)	Large Scale	16lb/ft ²	766 Pa
Manning's "n" ⁴ (Unvegetated)	Calculated	0.028	0.028
Seedling Emergence ⁴	ECTC Draft Method #4	296%	296%
ROLL SIZES		8.5 ft x 90 ft	2.6 m x 27.4 m

NOTES:

- The property values listed are effective 04/2011 and are subject to change without notice.
- MARV indicates minimum average roll value calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any sample taken during quality assurance testing will exceed the value reported.
- Maximum permissible velocity and shear stress has been obtained through vegetated testing programs featuring specific soil types, vegetation classes, flow conditions, and failure criteria. These conditions may not be relevant to every project nor are they replicated by other manufacturers. Please contact Propex for further information.
- Calculated as typical values from large-scale flexible channel lining test programs with a flow depth of 6 to 12 inches.



TESTED. PROVEN. TRUSTED.
www.geotextile.com

Propex Operating Company, LLC · 6025 Lee Highway, Suite 425 · PO Box 22788 · Chattanooga, TN 37422
ph 423 899 0444 · ph 800 621 1273 · fax 423 899 7619

Geotex[®], Landlok[®], Pyramat[®], X3[®], SuperGro[®], Petromat[®] and Petrotac[®] are registered trademarks of Propex Operating Company, LLC.

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by Propex for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by Propex and individual customers. Propex specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.