

WINFAB 370HP



WINFAB 370HP is manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position.

WINFAB 370HP resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV English	MARV Metric
Wide Width Tensile	ASTM D-4595	3600 x 3300 lbs/ft	52.5 x 48.2 kN/m
Wide Width Tensile (2% Strain)	ASTM D-4595	540 x 540 lbs/ft	7.9 x 7.9 kN/m
Wide Width Tensile (5% Strain)	ASTM D-4595	1500 x 1560 lbs/ft	21.9 x 22.8 kN/m
Wide Width Tensile (10% Strain)	ASTM D-4595	2400 x 2400 lbs/ft	35 x 35 kN/m
UV Resistance (500 hrs)	ASTM D-4355	80%	80%
Apparent Opening Size (AOS)*	ASTM D-4751	30 US Std. Sieve	0.60 mm
Permittivity	ASTM D-4491	.52 sec ⁻¹	.52 sec ⁻¹
Permeability	ASTM D-4491	.05 cm/sec	.05 cm/sec
Water Flow Rate	ASTM D-4491	40 gpm/ft ²	1630 lpm/m ²

*Maximum Average Roll Valve

Notes:

- Mullen Burst ASTM D-3786 has been removed. It is not recognized by ASTM D-35 on Geosynthetics.
- Puncture ASTM D-4833 has been removed. It is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D-6241

PROPERTY	Typical English	Typical Metric
Roll Dimensions	15 x 300 ft	4.6 x 91.5 m
Roll Area	500 yd ²	418 m ²

Disclaimer: Willacoochee Industrial Fabrics assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. Willacoochee Industrial Fabrics disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.

© 2013 Willacoochee Industrial Fabrics, Inc.

Willacoochee Industrial Fabrics, Inc.

PO Box 599 • 769 West Main Street • Willacoochee, GA 31650

Ph: (912) 534-5757 • Fax: (912) 534-5533

